



## OXIDIZED BITUMED

### Oxidized bitumen 115/15

SPECIFIC GRAVITY @25/25 C	approx. 1.05	D-70
PENETRATION @25 C	10/20	D-5
SOFTENING POINT C	110/120	D-36
DUCTILITY @25 C	1.5min	D-13
LOSS ON HEATING (wt)%	0.2Max	D-6
FLASH POINT C	260min	D-92
SOLUBILITY IN CS2 (wt)%	99min	D-4

### Oxidized bitumen 95/25

SPECIFIC GRAVITY @25/25 C	approx. 1.05	D-70
PENETRATION @25 C	20/30	D-5
SOFTENING POINT C	90/100	D-36
DUCTILITY @25 C	1.5min	D-113
LOSS ON HEATING (wt)%	0.2Max	D-6
FLASH POINT C	260min	D-92
SOLUBILITY IN CS2 (wt)%	99min	D-4

### Oxidized bitumen 90/15

SPECIFIC GRAVITY @25/25 C	approx. 1.05	D-70
PENETRATION @25 C	10/20	D-5
SOFTENING POINT C	85/95	D-36
DUCTILITY @25 C	1.5min	D-113
LOSS ON HEATING (wt)%	0.2Max	D-6
FLASH POINT C	260min	D-92
SOLUBILITY IN CS2 (wt)%	99min	D-4

**ADDRESS:** No61-Ofogh Building – Farahzadi Blvd – Tehran-Iran

**Tell:** +98 21 22132058

**WhatsApp:** +98 930 517 7388

**Email:** [info@saltakoil.com](mailto:info@saltakoil.com)

**Website:** [www.saltakoil.com](http://www.saltakoil.com)