



SALTAK OIL COMPANY

SN 500 BASE OIL

Property	Test method	Range
Kinematic viscosity @40 ^o c(cst)	Astm d-445	Tbr
Kinematic viscosity @ 100 ^o c(cst)	Astm d-445	11-12
Viscosity index	Astm d-2270	88(min)
Density @15 ^o c	Astm d-4052	0.885- 0.896
Flash point	Astm d-92	235(min)
Pour point	Astm d-97	-3 to -6
Tan (mg koh/gr)	Astm d-664	0.05
Carbon residue (%wt)	Astm d-189	0.05
Color	Astm d-1500	2.5 max
Copper corrosion(stage)	Astm d-130	1b
Water content(ppm)	Astm d-1744	100(max)
Demulsibility(c _c)	Astm d-1401	40/37β (15 min)
Foam(c _c)	Astm d-892	10/0 30/0 10/0
Noak volatility(%wt)	Astm d-5800	4 (max)
Aromatic content	Astm d-3238	10(max)

ADDRESS: No61-Ofogh Building – Farahzadi Blvd – Tehran-Iran

Tell: +98 21 22132058 ,

WhatsApp: +98 930 517 7388

Email: info@saltakoil.com

Website: www.saltakoil.com